

Anthracite 0.60 - 0.80  
 Typical Lab Analysis

SIEVE	Particle Size	% Passing
#6	3.35mm	100
#8	2.36mm	99.7
#10	2.00mm	99.3
#12	1.70mm	98.4
#14	1.40mm	96.8
#16	1.18mm	94.1
#18	1.00mm	78.6
#20	0.85mm	23.8
#25		5.5

Test	Result	Specification
Effective Size (mm)	0.78	0.60-0.80
Uniformity Coefficient	1.2	1.6
MOH Hardness	2.85	2.7 min.
Specific Gravity	1.6	1.6 min.
Acid Solubility	0.87%	5.00%
Caustic Solubility	1.46	2.00